

Fenochem Moulding Compound

T 5700 *Injection Grade* - HEAT RESISTANT -

Colour	:	black
Reinforcement	:	organic/inorganic
Application areas	:	handles, pan-handles, technical pieces
Mark	:	DIN 31/1649

PROPERTY	METHOD	UNIT	VALUE
Density	ISO 1183	g/cm ³	1.40
Mould. shrinkage	ISO 2577	%	0.5 - 0.7
Post - shrinkage	ISO 2577	%	0.4 - 0.6
Water absorption	ISO 62	mg	≤ 100
Flexural strenght	ISO 178	MPa	≥ 60
Charpy impact strenght	ISO 179	KJ/m ²	≥ 4.0
Charpy not. imp. strenght	ISO 179	KJ/m ²	≥ 1.5
Temper. of defl.under load	ISO 75	°C	≥ 140
Flammability (meth. BH)	IEC 707	CLASS	≤ BH 2 - 10
Surface resistance	IEC 93 -	Ohm	≥ 10 ⁹
Volume resistivity	IEC 93	Ohm • cm	≥ 10 ¹⁰
Proof-tracking index	IEC 112	V	≥ 175

Rev. Febbrary_2010

The information given in our datasheet, which to our knowledge is correct, does not constitute any kind of warranty or other undertaking of responsibility from Chemiplastica, but serves only as general information with respect to possible applicability of the products as well as the characteristics and handling of the products.

